

## BFKWN | Woolen Yarn

---

All colours in stock service

BFKWN          2/18          50 % Wool 40 % Blue Fox 10% Nylon          Woolen Yarn          08col.

---

### Minimums per colour

Stock service colour 1 kg

Own colours (TOP Dyed) 41kg ~

---

### Test appraisal certificate

We adhere to a rigorous quality control and inspection process from procuring raw materials to yarn production. We can furnish a 'Certificate of Test and Appraisal' detailing the testing methods following the Japanese Industrial Standards (JIS).

-Dyeing fastness test chart

We can provide inspection results for the dye-fastness of textiles and garments dyed by our company. These results are obtained through thorough examination following the test methods and grades outlined in the Japanese Industrial Standards (JIS).

---

### Recommended Milling Process

Pre-washing → Washing → Rinsing → Milling → Softening → Spin-drying → Drying

Temperature          36 - 42°C

Detergent          Anionic detergent (solution of 2 g/litre)

Bath ratio          1: 20

Spin-drying          160%

Drying          Natural Drying (Tumble Dry may be applied at the initial stage to smooth out creases. 55°C - 3 min. )

To account for potential variations in results based on equipment and yarn tension, we strongly recommend conducting a sample trial before initiating actual production.

### Care Instructions

Use a mesh laundry bag.

Do not iron directly.

