KHAAS | Worsted Yarn

All colours in stock service			
KHAAS 3/80 KHAAS 2/60		Worsted Yarn24col.Worsted Yarn24col.	

Minimums per colour

Stock service colour 1 kg Own colours (TOP Dye / Yarn Dye) $\,$ 3kg \sim

Test appraisal certificate

We adhere to a rigorous quality control and inspection process from procuring raw materials to yarn production. We can furnish a 'Certificate of Test and Appraisal' detailing the testing methods following the Japanese Industrial Standards (JIS). -Dyeing fastness test chart

We can provide inspection results for the dye-fastness of textiles and garments dyed by our company. These results are obtained through thorough examination following the test methods and grades outlined in the Japanese Industrial Standards (JIS).

Recommended Milling Process

$Pre-washing \rightarrow Washing \rightarrow Rinsing \rightarrow Milling \rightarrow Softening \rightarrow Spin-drying \rightarrow Drying$		
Temperature	36 - 42°C	
Detergent	Anionic detergent (solution of 2 g/litre)	
Bath ratio	1:20	
Spin-drying	160%	
Drying	Natural Drying (Tumble Dry may be applied at the initial stage to smooth out creases. 55° C $$ - 3 min.)	

To account for potential variations in results based on equipment and yarn tension, we strongly recommend conducting a sample trial before initiating actual production.

Care Instructions

Use a mesh laundry bag when washing by hand. Do not iron directly. Dry flat in the shade.



